

Technical Data Sheet – ASTM Standard

Lundhs Aurora Blue

Lundhs Aurora Blue is quarried in Ukraine. It is an Anorthosite with big blue crystals on a black background.

Technical Properties	Standard	Mean Values
stone name:		Anorthosite
structure:		coarse grained
texture:		oriented feldspar crystals with lustre
Compressive Strength	ASTM C-170	25,694 PSI
Flexural Strength	ASTM C-880	2,006 PSI
Abrasion Resistance	ASTM C-1353	113 wear index value
Water Absorption	ASTM C-97	0.12 %
Density	ASTM C-97	168.6 lb/ft ²
Modulus of Rupture	ASTM C-99	2,760 PSI

* PSI: Pounds Per Square Inch

** Method: American Society for Testing and Materials

Source: ABIC Testing Laboratories, Inc.